



## Effects of High-Temperature Annealing in Air on Hi-Nicalon Fiber-Reinforced Celsian Matrix Composites

By Narottam P. Bansal

BiblioGov. Paperback. Book Condition: New. This item is printed on demand. Paperback. 26 pages. Dimensions: 9.7in. x 7.4in. x 0.1in. BNSiC-coated Hi-Nicalon fiber-reinforced celsian matrix composites (CMC) were annealed for 100 h in air at various temperatures to 1200 C, followed by flexural strength measurements at room temperature. Values of yield stress and strain, ultimate strength, and composite modulus remain almost unchanged for samples annealed up to 1100 C. A thin porous layer formed on the surface of the 1100 C annealed sample and its density decreased from 3.09 to 2.90 g/cm<sup>3</sup>. The specimen annealed at 1200 C gained 0.43 wt%, was severely deformed, and was covered with a porous layer of thick shiny glaze which could be easily peeled off. Some gas bubbles were also present on the surface. This surface layer consisted of elongated crystals of monoclinic celsian and some amorphous phase(s). The fibers in this surface ply of the CMC had broken into small pieces. The fiber-matrix interface strength was characterized through fiber push-in technique. Values of debond stress,  $\alpha$ (sub d), and frictional sliding stress,  $\tau$ (sub f), for the as-fabricated CMC were 0.31-0.14 GPa and 10.4-3.1 MPa, respectively. These values...



[READ ONLINE](#)  
[ 5.87 MB ]

### Reviews

*A top quality publication along with the font used was intriguing to read. I really could comprehend everything using this written e book. Its been designed in a remarkably straightforward way and it is only after i finished reading through this publication by which basically altered me, modify the way i believe.*

*-- Cathrine Larkin Sr.*

*Very useful to all of group of people. I actually have read through and so i am certain that i will planning to study yet again once again down the road. I am just very easily can get a satisfaction of looking at a created book.*

*-- Mark Bernier*